

PREVIOUS DAY

TODAY

FOLLOWING DAY

12 13 14 15 16 17 18 19 20 21 22 23 24 1 2 3 4 5 6 7 8 9 10 11 12 13 14 15 16 17 18 19 20 21 22 23 24 1 2 3 4 5 6 7 8 9 10 11 12

Conversions

Celsius

-15 -10 -5 0 5 10 15 20 25 30 35

5 15 25 35 45 55 65 75 85 95

Fahrenheit

1 cm = 0.393 in. 1 in = 2.54 cm
 1 m = 1.094 yd 1 yd = 0.914 m
 1 l = 1.06 qt 1 qt = 0.94 l
 1 kg = 2.21 lb 1 lb = 0.45 kg




World Time Chart

Times Indicated Are Local Standard

- 1) Set time at your location.
- 2) Read time in desired city.

 **Spyderco** INC.
Golden, CO USA



D-2	G-2	M-2	W-2	O-1	ATS-34	AUS-6	AUS-8	MBS-26	RS30	154CM	440A	440B	440C	CPM 440V	1095		
1.40-1.60	0.90	0.76-0.88	0.85-1.5	0.85-1.0	1.05	0.55-0.65	0.70-0.75	0.85-1.0	1.0-1.12	1.05	0.6-0.75	0.75-0.95	0.95-1.2	2.15	0.9-1.03	0.5	(C) Carbon
0.05	0.60	0.15-0.4	0.1-0.4	1.0-1.4	0.40	1.00	1.00	0.30-0.60	0.50	0.50	1.00	1.00	1.00	0.40	0.3-0.5	0.	(Mn) Manganese
0.03	0.02	0.03	--	--	0.03	0.04	0.04	0.04	0.04	--	0.04	0.04	0.04	--	0.04	0.	(P) Phosphorus
0.02	0.03	0.03	--	--	0.02	0.03	0.03	0.01	0.015	--	0.03	0.03	0.03	--	0.05	0.	(S) Sulphur
11.0-13.0	15.5	3.75-4.5	0.15	0.4-0.6	14.0	13.0-14.5	13.0-14.5	13.0-15.0	12.5-14.5	14.0	16.0-18.0	16.0-18.0	16.0-18.0	17.0	--	0.	(Cr) Chromium
0.60	0.37	0.2-0.45	0.1-0.4	--	0.35	1.00	1.00	0.65	1.00	0.30	1.00	1.00	1.00	0.4	--	0.	(Si) Silicon
0.30	--	0.30	0.20	0.30	--	0.49	0.49	--	--	--	--	--	--	--	--	0.	(Ni) Nickel
1.10	--	1.75-2.25	0.15-0.35	0.30	--	0.1-0.25	0.1-0.25	--	0.15-0.25	--	--	--	--	5.50	--	0.	(V) Vanadium
0.7-1.2	0.30	4.5-5.5	0.10	--	4.0	--	0.1-0.3	0.15-0.25	0.4-0.55	4.0	0.75	0.75	0.75	0.4	--	0.	(Mo) Molybdenum
--	--	5.5-6.75	0.15	0.4-0.6	--	--	--	--	--	--	--	--	--	--	--	0.	(W) Tungsten

 **Spyderco** INC.
Golden, CO USA

Knife Steel Composition Comparison Guide
©1994
In % of total material

